



BioCorr® Rust Preventative



PRODUCT DESCRIPTION

BioCorr Rust Preventative is a waterbased, biobased, and biodegradable rust preventative that is intended for preservation of metals in storage and during transportation. BioCorr Rust Preventative provides multi-metal protection and is an excellent environmentally sound alternative to petroleum derived products. This ready-to-use formulation can provide protection for up to two years of indoor storage; or during shipments when combined with VpCI® packaging materials. Unlike rust preventative oils this product leaves a dry film on the surface of the metal that is virtually undetectable. This feature helps to create a clean workplace and prevents material waste. BioCorr Rust Preventative is VOC free and the formulation is biodegradable; eliminating expensive disposal costs associated with oils.

BioCorr Rust Preventative has been awarded USDA BioPreferredSM designation (www.preferred.gov).

FEATURES

- Provides excellent multi-metal corrosion protection
- Combines film-forming additives with Vapor phase Corrosion Inhibitors (VpCIs)
- Environmentally friendly and biodegradable
- Replaces hazardous mineral oils and flammable solvents
- VOC free
- Contains no chlorinated compounds, chromates, or nitrites
- Ready-to-use product
- Contains biostatic material

- Formulated with renewable raw materials, contains 64% biobased content
- USDA certified Biobased product

APPLICATION

BioCorr is a ready-to-use product and can be applied by dipping or spraying. BioCorr SC is supplied as a viscous concentrate and must be diluted and thoroughly mixed prior to use.

TYPICAL APPLICATIONS

- Biodegradable preservative for machines and equipment
- Temporary coating for storage and shipment
- Protection of pipes, flanges, gears
- Cast iron, sheets, and coils

TYPICAL PROPERTIES

BioCorr

Appearance	Milky white liquid
pH	8.4-9.1 (neat)
Density	8.3-8.4 lb/gal (1.00-1.01 kg/l)

BioCorr SC

Appearance	Clear amber liquid
pH	8.5-9.3 (1% water)
Density	7.8-7.9 lb/gal (0.93-0.95 kg/l)
NVC	89-93%

TEST RESULTS

ASTM D 1748 (Humidity Chamber), hours

Carbon Steel	Copper	Aluminum
600	160-200	160-200

ASTM D 4627-86 (Cast Iron Chip Test)
Pass



STORAGE AND PACKAGING

BioCorr Rust Preventative is packaged in 5 gallon (19 liter) pails, 55 gallon (208 liter) drums, liquid totes, and bulk.

Also available as EcoAir® BioCorr in 12 oz. (340 g) compressed air cans, 12 per carton.

The product should be stored sealed. Agitate before each use. The shelf life of BioCorr Rust Preventative is up to 24 months.

BioCorr SC is a viscous superconcentrate that should be diluted at 1:19 and thoroughly mixed prior to use.

BioCorr Green is available with green tint to aid in visual inspection.

Note: Please see the Safety Data Sheet (SDS) for proper handling of the product.

FOR INDUSTRIAL USE ONLY

KEEP OUT OF REACH OF CHILDREN

KEEP CONTAINER TIGHTLY CLOSED

NOT FOR INTERNAL CONSUMPTION

CONSULT SAFETY DATA SHEET FOR MORE

INFORMATION

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@corotecvci.com
Internet <http://www.corotecvci.com>

printed on recycled paper



100% post consumer

Revised: 12/17/13. ©Cortec Corporation 2004-2013. All rights reserved. Supersedes: 4/4/12.
© 2013, Cortec Corporation. All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. ISO accreditation applies to Cortec's processes only.

Distributed by:

**DAYS
EXPORT
PACKING**

55169 CR 3 North, Elkhart, IN 46514 USA

Phone (574) 264-4121

Fax (574) 262-3972

Toll Free (800) 424-8117

email: info@daysexportpacking.com

www.daysexportpacking.com